

HIKRA®

solar cables
part of HIS CONNECT™

HIKRA® SOL EN50618 (H1Z2Z2-K) IEC62930

DATA SHEET

**IN FOCUS IS THE PLANT REVENUE
IN OPERATION OUR SOLAR CABLES**

- Higher water resistance; Direct burial
- CPR compliant EN50575
- Global availability
- 25 Years expected lifetime
- Meter marking



HIS

we connect solar energy

HIKRA® SOL

TECHNICAL DATA



Construction	
Strand construction	Tin-plated copper strand (electrolytic copper), fine wire acc. IEC 60228 Class 5
Insulation	Electron-beam cross-linked Polyolefin; Shore hardness D 32
Outer Sheath	Electron-beam cross-linked special compound XLPO; Shore hardness D 36
Colour	Sheath: black, red; Insulation: clear – naturally colored
Marking	HIKRA SOL1500V H12222-K IEC62930 1x6,0mm ² R 50363076 CE <i>with meter marking</i>
Standards	EN50618 (H12222-K) TÜV R60148037; IEC62930 131

Technical characteristics	
Nominal voltage	1,5kV DC and 1,0kV AC
Maximum permitted operating voltage:	1,8kV DC (2,0 kV DC internal examination)
Voltage test on complete cable	6,5kV AC / 15kV DC (5 minutes water bath, 20±5°C)
Current carrying capacity	See document „Current rating – HIKRA® Solar Cable“ November 2013
Short-circuit-temperature	250° C/5s

Material properties	
UV stability	Tensile strength and ultimate-elongation after 720 h (360 cycles) ≥ 70% of initial values; EN 50289-4-17 acc. Method A; EN ISO 4892-1 (2000) and EN ISO 4892-2 (2006)
Ozone resistance	72h, relative humidity 55±5%, Temperature 40±2°C (EN 50396 Method B; Ozone concentration (200±50)x10 ⁻⁶)
Insulation resistance	Insulation resistance in water bath, each 2h at +90°C and 2h at 20°C (Limit values acc. EN 50618 Table 1)
Dynamic penetration test	Spring-steel-needle through insulation or sheath (EN50618 Annex D)
Direct burial	Long-term water immersion at 90°C, duration 12 weeks; Insulation resistance ≥ 3GΩ (internal examination acc. UL44 cl. 5.4 & UL2556 6.4.4.2.1)
Crushing- and impact-resistance	Impact-Resistance UL 854.23 and Crushing-Resistance UL 854.24 (internal examination)
Sheath resistance against acid and alkaline	168h at 23°C in N-Oxal acid and N-Sodium hydroxide (EN 60811-404); ammoniac-resistant
Behavior in case of fire	Flame-retardant acc. EN 60332-1-2 Annex A, low smoke emission (EN 61034,-2)
CPR-Performance	Dca; burning behavior acc. EN 50575:2014
Halogen-free	EN 50525-1, Annex B
Cold impact test	EN 60811-506, EN 50618 Annex C.1 at -40°C
Cold elongation test	Max. 30% elongation at -40±2°C, 16h (EN 60811-505)
Damp heat test	Duration 1000h at 90°C and min. 85% relative humidity (EN 60068-2-78)
Minimum bending radius flexible / fixed	10x cable diameter 4x cable diameter

Temperature Range	
Temperature	Ambient temperature: -40° C to +90°C; Maximum conductor temperature: +120° C
Maximum storage temperature	+40°C
Minimum temperature for installation	-25°C

Order No. black	Order No. red	Cross-section mm ²	Construction n x max.-Ø (mm)	Max. resistance (Ω/km)	External diameter (+/- 0,2 mm)	Copper index kg/km	Approx. Weight kg/km
739065	739066	1 x 1.5	29 x 0.25	13.7	4.6	14.0	32.0
738609	738610	1 x 2.5	47 x 0.25	8.21	5.0	24.0	42.0
738613	738614	1 x 4.0	52 x 0.3	5.09	5.4	38.4	57.0
738615	738616	1 x 6.0	78 x 0.3	3.39	6.0	57.6	76.0
738617	738618	1 x 10.0	77 x 0.4	1.95	7.2	96.0	119.0
738619	-	1 x 16.0	126 x 0.4	1.24	9.3	153.6	196.0
739061	-	1 x 25.0	190 x 0.4	0.795	11.3	240.0	291.0

www.his-solar.com

**Headquarter
Germany**

HIS Renewables GmbH
Siemensstraße 4
64760 Oberzent
T +49 60689314400
E info@his-solar.de

France

HIS Renewables
15 Avenue Emile Zola
74100 Annemasse
T +33 623293246
E guillaume.picat@his-solar.de

Spain

HIS Renewables
Avenida de Brasil 17
Madrid 28020
T +34 634285033
E carlos.fornes@his-solar.de

Turkey

HIS Solar Sistemleri A.S.
Alsancak Mah. 1479 Sk.15/17
35220 Konak Izmir
T +90 2324220931
E info@his-solar.com.tr